



# Hardener 807.0

## Field of Application

- Cross-linking component for membrane press glues KLEIBERIT Supratherm 430, 436

## Properties of Hardener 807.0

<b>Basis:</b>	Isocyanate
<b>Density:</b>	ca. 1.1 g/cm <sup>3</sup>
<b>Colour:</b>	transparent
<b>Viscosity at 25°C</b> (Brookfield RVT Sp 2/20 Upm):	1,400 ± 500 mPa·s
<b>Hardener Dosing:</b>	approx. 5 %
<b>Identification:</b>	According to the German hazardous substances regulations GefStoffV, contains aliphatic polyisocyanate (see our safety data sheet)

## Packaging

Carton 6 bottles, 0.5 kg net each  
Carton 12 bottles, 1.0 kg net each  
Metal canister, 5.5 kg net  
Metal can, 25 kg net

## Storage

KLEIBERIT Hardener 807.0 can be stored in factory sealed containers for approx. 9 months.  
Protect from humidity and frost!

EX1109; replaces previous versions



# KLEIBERIT®

KLEBSTOFFE • ADHESIVES

#### **Waste Disposal**

Disposal of contents and/or containers should comply with all applicable federal, state and local regulations.

Our containers are made of recyclable material.

#### **Service**

Our application department may be consulted at any time without obligation. The statements made herein are based on our experience gained to date. They are to be considered as information without obligation. Please test and establish for yourself the suitability of our products for your particular purposes. No liability exceeding the value of our product can be derived from the foregoing statements. This also applies to the technical consultancy service which is rendered free of charge and without obligation.